## AMENDMENTS TO THE CLAIMS



- 1.(Cancelled)
- 2.(Cancelled)
- 3.(Previously amended) Free radical emulsion polymerization method according to claim 13, wherein said dimer is selected from the group consisting of  $\alpha$ -methyl vinyl compounds and  $\alpha$ -ethyl vinyl compounds.
- 4.(Previously Amended) Free radical emulsion polymerization method according to claim 14, wherein said dimer is selected from the group consisting of  $\alpha$ -methyl vinyl compounds and  $\alpha$ -ethyl vinyl compounds.
- 5.(Previously Amended) Free radical emulsion polymerization method according to claim 13, wherein said dimer is selected from the group consisting of dimers or cross-dimers or α-methylstyrene, methyl methacrylate, hydroxy ethylacrylate, benzyl methacrylate, allyl methacrylate, methacrylate, methacrylate, methacrylate, methacrylate, methacrylate, methacrylate, isocyanatoethyl methacrylate, meta-isopopenyl-α,α-dimethyl isocyanate (TMI), ω-sulfoxyalkyl methacrylates and alkali salts thereof.
- 6.(Canceled)
- 7.(Canceled)
- 8.(Canceled)
- 9.(Canceled)

CI

10.(Canceled)

11.(Canceled)

12.(Canceled)

- 13.(Currently Amended) Free radical emulsion polymerization method for forming latex particles of a monomer or monomer mixture in a water-based reaction in the presence of a chain transfer agent and of a surfactant, wherein said surfactant is present in a concentration below twice its critical micelle concentration of at least least 0.5%, by weight, to-and that said chain transfer agent is a dimmer wherein said latex particle has an average particle size of less than 100 nm.
- 14.(Previously Added) Free radical emulsion polymerization method according to claim 13, wherein said surfactant is a non-ionic surfactant, present in a concentration versus said monomer or monomer mixture of from 5 up to 25 % by weight.
- 15.(Previously Added) Free radical emulsion polymerization method according to claim
  13, wherein said surfactant is an anionic surfactant, present in a concentration versus said
  monomer or monomer mixture of from 0.05 up to 10 % by weight.
- 16.(Previously Added) Free radical emulsion polymerization method according to claim
  13, wherein said surfactant is an anionic surfactant, present in a concentration versus said
  monomer or monomer mixture of from 0.05 up to 1%, by weight.

- 17.(Previously Added) Free radical emulsion polymerization method according to claim 15, wherein said dimer is a compound selected from the group consisting of α-methyl vinyl compounds and α-ethyl vinyl compounds.
- 18.(Previously Added) Free radical emulsion polymerization method according to claim 16, wherein said dimer is a compound selected from the group consisting of  $\alpha$ -methyl vinyl compounds and  $\alpha$ -ethyl vinyl compounds.
- 19.(Previously Added) Free radical emulsion polymerization method according to claim 14, wherein said dimer is a compound selected from the group consisting of dimers or cross-dimers of α-methylstyrene, methyl methacrylate, hydroxy ethylacrylate, benzyl methacrylate, allyl methacrylate, methacrylonitrile, glycidyl methacrylate, methacrylic acid, tert.-butyl methacrylate, isocyanatoethyl methacrylate, meta-isopopenyl-α,α-dimethyl isocyanate (TMI), ω-sulfoxyalkyl methacrylates and alkali salts thereof.
- 20.(Previously Added) Free radical emulsion polymerization method according to claim 15, wherein said dimer is a compound selected from the group consisting of dimers or cross-dimers or  $\alpha$ -methylstyrene, methyl methacrylate, hydroxy ethylacrylate, benzyl methacrylate, allyl methacrylate, methacrylonitrile, glycidyl methacrylate, methacrylic acid, tert.-butyl methacrylate, isocyanatoethyl methacrylate, meta-isopopenyl- $\alpha$ , $\alpha$ -dimethyl isocyanate (TMI),  $\omega$ -sulfoxyalkyl methacrylates and alkali salts thereof.

- 21.(Previously Added) Free radical emulsion polymerization method according to claim 16, wherein said dimer is a compound selected from the group consisting of dimers or cross-dimers or α-methylstyrene, methyl methacrylate, hydroxy ethylacrylate, benzyl methacrylate, allyl methacrylate, methacrylonitrile, glycidyl methacrylate, methacrylic acid, tert.-butyl methacrylate, isocyanatoethyl methacrylate, meta-isopopenyl-α,α-dimethyl isocyanate (TMI), ω-sulfoxyalkyl methacrylates and alkali salts thereof.
- 22.(Currently Amended) Free radical emulsion polymerization method according to claim
  13, wherein said monomers are selected from the group consisting of styrene derivatives,
  methacrylates, acrylates, methacrylamides, acrylamides, maleimides, vinyl ethers and
  vinyl esters.
- 23.(Previously Added) Free radical emulsion polymerization method according to claim 22, wherein said derivatives are selected from the group consisting of paramethylstyrene, tert.-butylstyrene, methylmethacrylate, ethylmethacrylate, butylmethacrylate, glycidylmethacryate, hydroxyethylmethacrylate, a-methylstyrene, ethylacrylate, butylacrylate, vinylacetate, vinyl versatate, butadiene, isoprene, acrylonitrile, methacrylonitrile, sulfoethyl methacrylate and its alkali salts, acrylic acid, methacrylic acid, tert-butyl acrylamide, AMPS, N-isopropylacrylamide, itaconic acid, maleic acid, maleic anhydride, vinylidene chloride, isopropylmethacrylate, dialkyl itaconate, acrylonitrile, methacrylonitrile and vinyl chloride.

- 24.(Previously Added) Free radical emulsion polymerization method according to claim

  14, wherein said non-ionic surfactants are selected from the group consisting of alcohol ethoxylates, alkylphenol ethoxylates, polyethylene oxide/polyethylene oxide block copolymers, polyvinyl alcohol, polyvinyl pyrrolidone, sorbitan fatty acid esters or sorbitan ester ethoxylates.
  - 25.(Previously Added) Free radical emulsion polymerization method according to claim 15, wherein said anionic surfactants are selected from the group consisting of fatty alcohol sulphates, alkylphenol sulphates, fatty alcohol ether sulphates, fatty alcohol ether sulphates, alkylphenol ether sulphates, alkylbenzene sulphonic acid, alkyl ether carboxylic acid and salts thereof, alkyl sulphosuccinates, alkyl sulphosuccinamates, phosphate esters or α-olefin sulphonates.
  - 26.(Previously Added) Free radical emulsion polymerization method for forming latex particles of a monomer or monomer mixture in a water-based reaction in the presence of a chain transfer agent and of a surfactant, wherein said surfactant is present in a concentration below twice its critical micelle concentration of at leat 0.5%, by weight, to and that said chain transfer agent is a cobalt complex.
  - 27.(Previously Added) Free radical emulsion polymerization method according to claim 26, wherein said surfactant is a non-ionic surfactant, present in a concentration versus said monomer or monomer mixture of from 5 up to 25 % by weight.

- 28.(Previously Added) Free radical emulsion polymerization method according to claim 27, wherein said non-ionic surfactants are selected from the group consisting of alcohol ethoxylates, alkylphenol ethoxylates, polyethylene oxide/polyethylene oxide block copolymers, polyvinyl alcohol, polyvinyl pyrrolidone, sorbitan fatty acid esters or sorbitan ester ethoxylates.
- 29.(Previously Added) Free radical emulsion polymerization method according to claim
  26, wherein said surfactant is an anionic surfactant, present in a concentration versus said
  monomer or monomer mixture of from 0.05 up to 10 % by weight.
- 30.(Previously Added) Free radical emulsion polymerization method according to claim 29, wherein said anionic surfactants are selected from the group consisting of fatty alcohol sulphates, alkylphenol sulphates, fatty alcohol ether sulphates, fatty alcohol ether sulphates, alkylphenol ether sulphates, alkylbenzene sulphonic acid, alkyl ether carboxylic acid and salts thereof, alkyl sulphosuccinates, alkyl sulphosuccinamates, phosphate esters or α-olefin sulphonates.
- 31.(Previously Added) Free radical emulsion polymerization method according to claim 26, wherein said surfactant is an anionic surfactant, present in a concentration versus said monomer or monomer mixture of from 0.05 up to 1%, by weight.
- 32.(Previously Added) Free radical emulsion polymerization method according to claim 26, wherein said monomers are selected from the group consisting of styrene derivatives,

 $\mathcal{O}($ 

methacrylates, acrylates, methacrylamides, acrylamides, maleimides, vinyl ethers and vinyl esters.

- 33.(Previously Added) Free radical emulsion polymerization method according to claim 32, wherein said derivatives are selected from the group consisting of paramethylstyrene, tert.-butylstyrene, methylmethacrylate, ethylmethacrylate, butylmethacrylate, glycidylmethacryate, hydroxyethylmethacrylate, a-methylstyrene, ethylacrylate, butylacrylate, vinylacetate, vinyl versatate, butadiene, isoprene, acrylonitrile, methacrylonitrile, sulfoethyl methacrylate and its alkali salts, acrylic acid, methacrylic acid, tert-butyl acrylamide, AMPS, N-isopropylacrylamide, itaconic acid, maleic acid, maleic anhydride, vinylidene chloride, isopropylmethacrylate, dialkyl itaconate, acrylonitrile, methacrylonitrile and vinyl chloride.
- 34.(Previously Added) Free radical emulsion polymerization method according to claim 26, wherein said cobalt complex is a cobalt III or cobalt III complex.
- Free radical emulsion polymerization method according to claim 35.(Previously Added) 34, wherein said cobalt complex is selected from cobalt II diphenyl cobaltate  $\Pi$ complex; bis(borondifluorodiphenylglyoximate) [bis[m-(2,3-butanedione bis(borondifluorodimethylglyoximate) cobaltate II complex; dioximato)(2-)O,O'tetraflorodiborato(2-propyl)N,N',N'',N'''](2-propyl)Co(III)]] or III.benzylbis(dimethlglyximato)(pyridine)cobalt

## **CONCLUSIONS**

Claims 3-5 and 13-35 are pending in the present application. All claims are believed to be in condition for allowance. A notice of allowance for claims 3-5 and 13-35 is respectfully requested.

September 17, 2003

Respectfully submitted,

Joseph T. Guy, Ph.D. Agent for Applicants

Régistration Number 35,172 NEXSEN PRUET JACOBS & POLLARD, LLC

P.O. Box 10648

Greenville, SC 29603 Telephone: 864-370-2211

Facsimile: 864-282-1177